

## CLAIMS

That which is claimed is:

1. A thermoplastic comprising between 70-75% syndiotactic polypropylene, wherein said thermoplastic exhibits a crystallization temperature of at least 71°C when tested pursuant to a modified ASTM Test Method D-794-85, wherein the cooling rate is 20°C/min.
2. The thermoplastic of Claim 1 wherein said crystallization temperature is at least 74°C.